



钢铁之家

www.steels.org.cn

# 全球钢号百科!

Global Steel Grade Encyclopedia



涵盖的行业或国家与地区类别



美国材料与试验协会

GJB

国家军用标准



动力机械工程师协会

EU

前欧洲标准化

AISI

美国钢铁学会



德国工业标准

AMS

航空航天材料规范



国际标准

JASO

日本汽车标准组织

EN

欧洲标准

JB

中国机械行业标准

UNS

统一编号系统

UNI

意大利标准



美国机械工程师协会

SS

瑞典标准



国家标准



日本工业标准

# Thermodur 2342 EFS

X35CrMoV5-1-1

C 0.35 Si 0.80 Cr 5.00 Mo 1.00 V 0.85

## Steel properties

Excellent high-temperature toughness, thermal conductivity, low susceptibility to hot cracking, may be water-cooled to a limited extent.

## Physical properties

### Coefficient of thermal expansion

at °C	20 – 100	20 – 200	20 – 300	20 – 400	20 – 500	20 – 600	20 – 700
$10^{-6} \text{ m/(m} \cdot \text{K)}$	10.9	11.9	12.3	12.7	13.0	13.3	13.5

### Thermal conductivity

at °C			
$\text{W/(m} \cdot \text{K)}$	20	350	700
	24.5	26.8	28.8

## Applications

Mandrel bars, pressure casting dies, and extrusion tools.

## Heat treatment

**Soft annealing °C**  
750 – 800

**Cooling**  
Furnace

**Hardness HB**  
max. 230

**Hardening °C**  
1000 – 1040


**Quenching**  
Air, oil or  
hot bath, 500 – 550 °C

**Hardness after quenching HRC**  
53

**Tempering °C**  
**HRC**

100	200	300	400	500	550	600	650	700
52	50	49	49	50	49	46	36	26

## Time-temperature-transformation diagram



## Tempering diagram/High-temperature strength diagram

